

3M™ Boron Nitride Suspension WP

3M™ Boron Nitride Suspension WP is a waterbased boron nitride coating. The use of refractory binders ensures good adhesion at high temperatures.

Typical application

Applied to metals:

- For tools (ladles, skimmers)
- For thermocouple protection tubes
- For measuring probes

Applied to refractory materials:

- For hot top rings
- For slide and float valves
- For nozzles, stoppers and runners

Advantages

- Excellent release agent, especially in applications with non ferrous melts
- Reduction of erosion by the melt and therefore reduced carryover of ferrous contaminants into the melt
- Excellent adhesion
- Improvement of billet surface quality
- Life improvement for hot top rings as well as slide and float valves
- Extension of maintenance and lubrication intervals
- Free of additives detrimental to health

Specification

Product data	3M™ Boron Nitride Suspension WP
Color	white
Powder constituent (BN)	≤ 12%
Liquid phase	water
pH value	6
Bonding agent	inorganic binder*
Density	1.03 – 1.06 g/cm ³
Viscosity	mean viscosity
Application temperature	1,400°C vacuum, 900°C in air

* must not be used on carbon surfaces and reducing atmosphere

Properties

3M™ Boron Nitride Suspension WP is particularly suitable for the coating of dense metallic, refractory and insulating materials. Due to the use of boron nitride of high chemical purity it is possible to achieve temperature resistant, stable coatings with excellent release and lubricating properties. These properties are retained even when in direct contact with molten metal and slag, especially for non ferrous applications.

The coating can therefore be seen to protect the coated surface by reducing wear and improving sliding properties. Coatings with boron nitride are temperature resistant to around 900°C in air. The coating shows good thermal conductivity and is electrically insulating.

Health and safety

Due to its chemical composition, this product is not classified as hazardous by the relevant regulations. However, normal safety and industrial hygiene precautions in the use of chemical products should be applied.

For further information please refer to the applicable health and safety data sheet.

Processing

3M™ Boron Nitride Suspension WP can be applied by brushing, rolling, dipping or spraying. Smooth and dense materials, such as metals and glass, are best coated by spraying, which has the additional benefit of achieving the best surface finish. Porous surfaces with higher absorption characteristics, such as refractory materials, are best coated by brushing, roller or spraying. The parts to be coated should be dry and free from dust, oil and grease as well as any residues of paints and lacquers. To prevent the formation of cracks, it is recommended that a thin coating giving full coverage be applied. The drying time is temperature dependant and can be considerably shortened by heating of the components to be coated either before or after coating.

Should more than one coat be required (by brush or roller application), it is recommended that the component be preheated to ensure correct adhesion, especially of the base coat. It is essential that the coating has fully dried prior to use. It is not necessary to burn the coating. Tools and equipment can be cleaned in water. Should the BN-Suspension remain unused for a period of time, the container should be briefly shaken to counter the effects of settling. These recommendations are intended to act as a guideline only, and are given in good faith to our best knowledge and belief. Process conditions can vary depending on the application.

Product is manufactured and sold by 3M Technical Ceramics, Zweigniederlassung der 3M Deutschland GmbH.

Warranty and Limitation of Liability: Many factors beyond our control and uniquely within user's knowledge and control can affect the use and performance of the product in a particular application. User is solely responsible for evaluating the product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of the product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, we warrant that each product meets the applicable product specification at the time we ship the product.

WE MAKE NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.

The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Limitation of Liability: Except where prohibited by law, we will not be liable for any loss or damages arising from the product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. We accept liability for intent and gross negligence. We are also liable for any culpable breach of major contractual obligations; however, if a breach of major contractual obligations is due to negligence, our liability is limited to the foreseeable damage associated with this type of contract. This does not affect our liability for culpable fatal or bodily injury or damage to health; this also applies to liability under the Product Liability Act (*Produkthaftungsgesetz*). Other claims for compensation are excluded.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by us are based on tests or experience that we believe are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any of our or third party intellectual property rights is granted or implied with this information.



3M Technical Ceramics
Zweigniederlassung der
3M Deutschland GmbH
Max-Schaidhauf-Straße 25
87437 Kempten, Germany
T +49 (0)831 5618-0
F +49 (0)831 5618-345
info.technical-ceramics@3M.com
www.3M.de / Technical-Ceramics

The management system has been certified according to DIN EN ISO 9001, DIN EN ISO 50001, DIN EN ISO 14001.

Please recycle. Printed in Germany.
© 3M 2015. All rights reserved.
Issued: 09/15

Storage

Containers should be kept tightly closed and, due to the water base, should be protected from frost.

Availability

3M™ Boron Nitride Suspension WP is available in polyethylene canisters of 10 kg capacity.

Larger quantities can be supplied in agreed batches.

**3M is a trademark of 3M.
Used under license by
3M subsidiaries and affiliates.**